

RHEOBUILD[®] 1115

(Formerly known as RHEOBUILD SP1iS)

High-range, retarding superplasticiser for high performance concrete mixes

Description

RHEOBUILD 1115 is composed of synthetic polymers specially designed to allow considerable reduction of mixing water while maintaining control on extend of set retardation.

RHEOBUILD 1115 is preferred admixture for triple blend binder system based high performance concrete (HPC) mixes or mixes containing micro silica or metakaolin.

RHEOBUILD 1115 is chloride free.

Uses

- Concrete containing Silica fume/ Metakaolin
- Ready mixed concrete
- Congested/complex reinforced sections
- Pre-cast concrete production
- Long-distance transporting
- Pumped concrete
- Low water/binder ratio mixes
- Mixes requiring >20% water reductions

Advantages

- Good dispersion even in mixes with high fines
- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Resistance to segregation even at high workability
- Extended setting with longer workability
- Reduced water content for a given workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability
- Supplied in powder form – does not freeze
- Reduced shrinkage and creep
- Increased ease in finishing concrete

Typical Properties *

Aspect	: Brown free flowing liquid
Relative Density	: 1.15 ± 0.02 at 25°C
pH	: ≥ 6
Chloride ion content	: < 0.2%

* Test values are obtained using water: powder ratio 69: 31

Standards

- ASTM C-494 Type G
- EN 934-2: T11.1/11.2
- IS 9103

Specification Clause

The high-range, retarding, superplasticising admixture for concrete shall be RHEOBUILD 1115, a sulphonated naphthalene polymer based formulation having slump retaining capabilities. The product shall be obtained by mixing with water at a ratio of 31:69 by weight before use. The product shall comply with IS:9103 and shall be of type G when tested to ASTM C-494.

Direction for use

RHEOBUILD 1115 is supplied in premix powder form, when mixed at site with water at a ratio of 31:69 by weight it produces a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the damp concrete after 50 to 70% of the mixing water has been added. The addition of RHEOBUILD 1115 to dry aggregate or cement is not recommended.

Dosage

Optimum dosage of RHEOBUILD 1115 should be determined with trial mixes. As a guide, a dosage range of 600ml to 1800ml per 100kg of cementitious material is normally recommended. Because of variations in concrete materials, job site conditions, and/or applications, dosages outside of the recommended range may be required. In such cases, contact your local BASF representative.

For addition information on RHEOBUILD 1115 admixture or on its use in developing concrete mixes with special performance characteristics, contact your local BASF representative.

Effects of over dosage

A severe over-dosage of RHEOBUILD 1115 can result in the following:

- Long extension of initial and final set
- Increase in air entrainment
- Bleed/segregation of mix, quick loss of workability
- Increased plastic shrinkage

A slight overdosing may not adversely affect the ultimate strength of the concrete and can achieve higher strengths than normal concrete, provided it is properly compacted and cured. Due allowance should be made for the effect of fluid concrete pressure on form work, and stripping times should be monitored.

In the event of over dosage, consult your local BASF representative immediately.

Compatibility

RHEOBUILD 1115 is compatible with most admixtures used in the production of quality concrete including normal, other mid-range and high-range water-reducing admixtures, air entrainers, accelerators, retarders, extended set-control admixtures, corrosion inhibitors, and shrinkage reducers.

RHEOBUILD 1115 is also compatible with slag and pozzolans such as fly ash, metakaolin and silica fume.

Corrosivity – Non Corrosive

RHEOBUILD 1115 admixture will neither initiate nor promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanized steel floor and roof systems. Neither calcium chloride nor any calcium chloride-based ingredients are used in the manufacture of RHEOBUILD 1115 admixture. In all concrete application, RHEOBUILD 1115 admixture will conform to the most stringent or minimum chloride ion limits currently suggested by construction industry standards and practices.

Workability

RHEOBUILD 1115 ensures that rheoplastic concrete remains workable in excess of 3 hours at +25°C. Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability.

It is strongly recommended that concrete should be properly cured particularly in hot, windy and dry climates.

The use of MASTERKURE 111CF, evaporation reducer to prevent quick moisture loss from the surface of the flat works such as pavements in the dry, windy and hot climates is highly recommended.

Packaging

RHEOBUILD 1115 is supplied in 25 kg bag.

Storage and Shelf life

RHEOBUILD 1115 must be stored where temperatures do not drop below +5°C. Store under cover, out of direct sunlight and protect from extremes of temperature.

Shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult your local BASF representative.

Safety precautions

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs (which can also be tainted with vapour until product fully cured or dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. Do not reuse containers for storage of consumable item. For further information refer to the material safety data sheet. MSDS available on demand or on BASF construction chemicals web site.

Note

All BASF Technical Data Sheets are updated on regular basis; it is the user's responsibility, to obtain the most recent issue.

Field services where provided, does not constitute supervisory responsibility, for additional information contact your local BASF representative.

Disclaimer

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

TDS Ref. no.: Rbdx1115/03/0109

BASF India Limited

Construction Chemicals Division

Plot No.37, Chandivali Farm Road, Chandivali, Andheri(East)

Mumbai – 400072 India

Tel: +91 22 28580200, Fax: +91 22 28478381

e-mail: basfcc@vsnl.net www.basf-cc.co.in Page 2 of 2

