



The Chemical Company

RHEOFIBRE®

Specification

Concrete shall be manufactured using crack controlling additive such as RHEOFIBRE®, a polypropylene fibre with an individual fibre length of 12mm and thickness of 18 microns.

Addition rate

0.6kg/m³

Effects of overdosing

Overdosing of RHEOFIBRE® will generally produce a reduction in workability, and an increase in the cohesiveness of the mix.

Storage

Should be stored in dry conditions.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

09/99 BASF_CC-UAE revised 04/2004

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

www.basf-cc.ae

Fax: +971 4 8851002

e-mail: marketingcc.mideast@basf.com



Certificate No.
963680



Certificate No.
945787



Certificate No.
772556